

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.

1/5/1

DIALOG(R)File 351:DERWENT WPI

(c) 2000 Derwent Info Ltd. All rts. reserv.

007339374

WPI Acc No: 87-336380/\*198748\*

XRAM Acc No: C87-143533

**polyAcrylic adhesive compsn. - has rapid curing rates and improved bond strengths**

Patent Assignee: BP CHEM LTD (BRPE )

Inventor: TAYLOR S A

Number of Countries: 009 Number of Patents: 003

Patent Family:

Patent No	Kind	Date	Applicat No	Kind	Date	Main IPC	Week
EP 247726	A	19871202	EP 87303603	A	19870423		198748 B
US 4775727	A	19881004	US 8741673	A	19870423		198842
JP 63275686	A	19881114	JP 87107878	A	19870430		198851

Priority Applications (No Type Date): GB 8610659 A 19860501; GB 8610526 A 19860430

Cited Patents: A3...8835; FR 2508924; GB 2061294; No-SR.Pub

Patent Details:

Patent	Kind	Lan	Pg	Filing	Notes	Application	Patent
--------	------	-----	----	--------	-------	-------------	--------

EP 247726	A	E	5				
-----------	---	---	---	--	--	--	--

Designated States (Regional): BE DE ES FR GB IT NL

US 4775727	A		4				
------------	---	--	---	--	--	--	--

Abstract (Basic): EP 247726 A

An adhesive compsn. comprises of (I) an acrylic functional urethane elastomer, derivable by reactive a polyether diol with an aromatic diisocyanate (pref. diphenyl methane diisocyanate) to form an isocyanate prepolymer (pref. with 2-20 % free isocyanate gps.) which is reacted with a molar excess (pref. up to 50% molar excess) of an acrylic monomer in the presence of a low molecular wt. di(meth)acrylate ester of a glycol, pref. used in 10-20 parts per 100 parts of prepolymer, (II) an acrylic monomer, (III) one or more organic cpds., selected from organic sulphimides (R-SO<sub>2</sub>-NH-COR<sub>1</sub> where R = aliphatic, alicyclic or aromatic gp. and R<sub>1</sub> = alicyclic or aromatic gp.), sulphinates (R-SO<sub>2</sub>-R<sub>2</sub> where R<sub>2</sub> = proton or monovalent metal ion) and salts thereof, (IV) a peroxide initiator and (V) a curing accelerator characterised in that it is an organic dye which is (a) capable of being solubilised in the adhesive resin derived by the addn. of (II) to (I) and (b) has at least 2 tertiary nitrogen atoms linked by one or more conjugated double bonds in its structure.

More specifically, the polyether diol is selected from polyoxyethylene glycol and polyoxypropylene glycol and has a molecular wt. from 400-2000. The di(meth)acrylate ester is of glycol selected from triethylene glycol, tetraethylene glycol, 1,3-butylene glycol and diethylene glycol. It is selected from a vinyl carboxylic acid and hydroxyalkyl(meth)acrylates, pref. from hydroxyethylacrylate, hydroxyethylmethacrylate, hydroxypropyl methacrylate, acrylic acid and methacrylic acid, and is added to I in an amount from 10-200% w/w of I. V is selected from methylene blue and crystal violet and is pref. used as a quat. ammonium salt, used in 0.1-2 part per 100 parts adhesive resin.

ADVANTAGE - This adhesive compsn. is curable aerobically, and has faster curing rates and improved bond strengths when compared with those of prior art.

Title Terms: POLYACRYLIC; ADHESIVE; COMPOSITION; RAPID; CURE; RATE; IMPROVE ; BOND; STRENGTH

Derwent Class: A14; A81; E19; G03

International Patent Class (Additional): C08F-220/00; C08L-075/08;

C09J-003/14

File Segment: CPI

?

(10)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets

(11) Publication number:

**0 247 726  
A2**

(12)

## EUROPEAN PATENT APPLICATION

(21) Application number: 8730360.1.2

(51) Int. Cl. 4: C09J 3/14, C08F 220/00

(22) Date of filing: 23.04.87

(30) Priority: 30.04.86 GB 8610526  
01.05.86 GB 8610659

(43) Date of publication of application:  
02.12.87 Bulletin 87/49

(84) Designated Contracting States:  
BE DE ES FR GB IT NL

(71) Applicant: BP Chemicals Limited  
Belgrave House 76 Buckingham Palace Road  
London, SW1W 0SU(GB)

(72) Inventor: Taylor, Stephen Alan  
BP Chemicals Ltd. Hayes Road Sully  
Penarth South Glamorgan CF6 2YU(GB)

(74) Representative: Krishnan, Suryanarayana  
Kalyana et al.  
BP INTERNATIONAL LIMITED Patents &  
Agreements Division Chertsey Road  
Sunbury-on-Thames Middlesex TW16  
7LN(GB)

### (54) Rapid cure acrylic adhesive compositions.

(57) This invention relates to an adhesive composition comprising (a) an acrylic functional urethane elastomer, (b) an acrylic monomer, (c) an organic sulphimide, an organic sulphinate or a salt thereof, (d) a peroxide initiator and (e) a tertiary amine curing accelerator. Component (e) preferably has at least two tertiary nitrogen atoms in its structure and is a reactive organic dye. The adhesive composition is curable aerobically, has faster curing rates than achieved hitherto and shows improved bond-strengths when compared with conventional tertiary amine curing accelerators.

EP 0 247 726 A2

RAPID CURE ACRYLIC ADHESIVE COMPOSITIONS

The present invention relates to improved rapid cure acrylic adhesive compositions.

Acrylic adhesive compositions are well known in the art. These compositions usually contain an acrylic functional urethane elastomer and an acrylic monomer which together form an adhesive resin, a peroxide initiator and a curing agent. Conventional compositions used hitherto have relatively long curing times.

It is an object of the present invention to formulate acrylic adhesive compositions which have a rapid curing rate by the use of novel accelerators.

Accordingly, the present invention is an adhesive composition comprising:

- (1) an acrylic functional urethane elastomer,
- (2) an acrylic monomer,
- (3) one or more organic compounds selected from organic sulphimides, organic sulphinates and salts thereof,
- (4) a peroxide initiator and
- (5) a curing accelerator characterised in that the curing accelerator is a reactive dye which is (a) capable of being solubilised in the adhesive resin derived by the addition of the acrylic monomer (2) to the urethane elastomer (1) and (b) has at least two tertiary nitrogen atoms linked by one or more conjugated double bonds in its structure.

The acrylic functional urethane elastomer (1) can be prepared by reacting a polyether diol such as e.g. polyoxyethylene glycol or polyoxypropylene glycol with an aromatic diisocyanate to form an isocyanate prepolymer.

In forming the isocyanate prepolymer, the polyether diol used suitably has a molecular weight in the range of 400-2000. The diol is reacted with an aromatic diisocyanate in the presence of a free radical stabilizer such as paramethoxy phenol. The aromatic diisocyanate used may for example be diphenyl methane diisocyanate (also known as "MDI"). Of the total isocyanate groups in the isocyanate prepolymer, it is desirable to have from 2-20%, preferably around 5%, free isocyanate groups.

The isocyanate prepolymer so formed is reacted with a molar excess of an acrylic monomer such as e.g. a hydroxyalkyl (meth)acrylate, specifically hydroxyethyl acrylate, hydroxyethyl methacrylate or hydroxypropyl methacrylate.

It is preferable to use up to 50% molar excess of the acrylic monomer with respect to the free isocyanate groups in the isocyanate prepolymer. This reaction is suitably carried out in the presence of a low molecular weight di(meth)acrylate ester of a glycol e.g. a dimethacrylate of triethylene glycol, tetraethylene glycol, 1,3-butylene glycol or diethylene glycol. This ester preferably has a molecular weight from 600 to 2000. The amount of dimethacrylate ester used is suitably from 10-20 parts per hundred parts of the prepolymer.

The resultant product is the acrylic functional urethane elastomer (1) to which is added to acrylic monomer (2) to form an adhesive resin. Examples of acrylic monomers that may be used include vinyl carboxylic acids and hydroxyalkyl (meth)acrylates. Specifically, these may be selected from hydroxyethyl acrylate, hydroxyethyl methacrylate, hydroxypropyl methacrylate, acrylic acid and methacrylic acid. The amount of acrylic monomer (2) added to the elastomer (1) is suitably from 20-40% by weight of the elastomer.

The organic sulphimides, organic sulphinates and salts thereof (3) used are preferably at least partially soluble in the adhesive resin. The organic sulphimides suitably have a formula:



wherein R is an aliphatic, alicyclic or an aromatic group and where R<sup>1</sup> is suitably an alicyclic or an aromatic group. Specific examples of such sulphimides include orthobenzene sulphimide. These sulphimides can be used as their salts e.g. sodium salts. The organic sulphinates and their salts suitably have a general formula:



where R has the same significance as for a sulphimide defined above and R<sup>2</sup> is either a proton or a monovalent metal ion e.g. ions of the alkali metals. Examples of the organic sulphinates and their salts include sodium benzene sulphinate.

It is preferably to use an equiweight amount of the sulphimide and sulphinate in the resin (e.g. 50/50) at a level of 0.5-2% by weight of the resin.

The peroxide initiator (4) used should be stable at room temperature and is suitably an organic peroxide, preferably an organic hydroperoxide such as e.g. t-butyl peroxide or cumene hydroperoxide. The peroxide initiator is suitably used in an amount from 1-3 parts per hundred parts of the adhesive resins.

The curing accelerator (5) is an organic dye which is (a) capable of being solubilised in the adhesive resin and (b) has at least two tertiary nitrogen atoms linked by conjugated double bonds in its structure.

The dyes are suitably used in the form of their salts e.g. quaternary ammonium halides to enhance solubility.

It is preferable for the dye to contain a high degree of functionality, e.g. the tertiary nitrogen atoms being linked by conjugated double bonds. Specific examples of such organic dyes include Methylene Blue and Crystal Violet. It will be appreciated by those skilled in the art that both these dyes contain at least two tertiary nitrogen atoms, conjugated double bonds linking the two nitrogen atoms, and aromatic ring structures for electron delocalisation.

The organic dyes are suitably used in an amount from 0.1-2 parts per hundred parts of the adhesive resin. The ability of the dyes to cure the resins is particularly enhanced if the curing is initiated photochemically, e.g. in the presence of visible light. Their high reactivity and ability to speed up cure means that use of high levels of the dye may result in uncontrollable cure rates.

In view of the high reactivity between the sulphimides and/or sulphinates (3) and the reactive organic dyes (5), these two components, (3) and (5) should not be allowed to come into contact in the adhesive composition except immediately prior to or at the point of use of the adhesive composition.

Thus it is preferably to store or market the components of this composition as a twin-pack system in any combination but ensuring that the dye (5) and the sulphimide and/or sulphinate (3) are not in the same pack.

For instance, in one pack the adhesive resin (components (1) and (2)) and the organic sulphimide and/or sulphinate (3) may be mixed whereas in the other pack the adhesive resin (components (1) and (2)) may be mixed with the peroxide and the reactive organic dye. In this case, the adhesive is used as a 50:50 mixture by weight of each pack. In use, contents of the two packs are mixed immediately prior to application.

Alternatively, the reactive organic dye may be in a separate pack from the remainder of the components. In this case, it is possible to apply a solution of the organic dye on to the substrate to be bonded. The solution of the dye used is suitably a dilute solution in a volatile solvent such as e.g. 1,1,1-trichloroethane. In this case the dye solution is applied to the substrate to be bonded, the solvent allowed to evaporate leaving a thin coating of the dye behind and then the remaining components of the adhesive are applied onto the dye coated substrate.

The adhesive compositions of the present invention are curable aerobically.

It has been observed that the bond strength of the bonded products resulting from the use of the adhesive composition of the present invention is significantly better than that achieved with adhesives containing the conventional amine curing agent.

The present invention is further illustrated with reference to the following Examples:-

The results are shown below in respect of time elapsed before the adhesive acquired adequate handling strength.

#### 40 Example 1

A mixture of diphenyl methane diisocyanate (30.4% w/w), triethylene glycol dimethacrylate (14.3% w/w) and paramethoxy phenol (200 ppm) was intimately mixed with polyoxypropylene glycol (mol wt 425, 35.9% w/w) over 1 hour. To this mixture hydroxyethyl acrylate (19.45 w/w) was added over 10 minutes and the entire mixture heated at 60°C for 6-8 hours to form the acrylic functional urethane elastomer.

The elastomer so formed was cooled to ambient temperature. Thereafter, hydroxyethyl acrylate (35 phr, based on elastomer) and methacrylic acid (20 phr, based on the elastomer) were added to the elastomer to form the adhesive resin.

The resulting adhesive resin was formulated into a twin pack adhesive composition (50/50 w/w of each pack) containing the following ingredients in each pack and tested in daylight for cure rates.

#### Pack 1

Adhesive resin (as above) 100 phr  
o-benzoic sulphimide 0.5  
Sodium benzenesulphinate 0.5  
Cumene hydroperoxide 3.0

Pack 2

Adhesive resin (as above) 100 phr  
Curing agent 0.5 phr

5 The following cure times are obtained (for handling strength) using the various curing agents listed below:

	<u>Curing Agent</u>	<u>Cure Time (min)</u>
10	N,N-bis-(2-hydroxyethyl)-p-toluidine	10-20
	Methylene Blue	2-3
	Crystal Violet	2-3
	None	no cure even after 4 hours

15

The above results show that use of an organic dye such as Methylene Blue and Crystal Violet according to the invention have a far superior cure rate compared with conventional curing agents.

20 Examples 2 and 3

In these Examples and the additional Comparative Tests the adhesive resin, the organic sulphimide/salt and the peroxide used were the same as that in Example 1 above. The tertiary amine curing agents used and the results achieved are tabulated below. The lap shear data given below was determined under  
25 standard test conditions as prescribed in British Standard No. BS 5350, Part C-5, 1976.

	<u>Example</u>	<u>Tertiary Amine</u>	<u>Curing Time (min)</u>
30		N,N-bis(2-hydroxyethyl)-p-toluidine*	10-20
	2	Methylene Blue	2-3
	3	Crystal Violet	2-3

\*Comparative Test not according to the invention.

35

Bond Strength Tests

	<u>Tertiary Amine</u>	<u>Surface Treatment</u>	<u>Lap Shear/Nmm<sup>-2</sup></u>
40	N,N-bis(2-hydroxyethyl)-p-toluidine*	as received	5.5
		grit blasted	9.2 - 17.6
	Methylene blue	as received	19.5 - 21.8
		grit blasted	20.4 - 23.0
	Crystal Violet	as received	16.2 - 20.1

45

\*Comparative Test not according to the invention.

Claims

50

1. An adhesive composition comprising:

(1) an acrylic functional urethane elastomer,

(2) an acrylic monomer,

(3) one or more organic compounds selected from organic sulphimides, organic sulphinates and salts

55 thereof,

(4) a peroxide initiator and

(5) a curing accelerator characterised in that the curing accelerator is an organic dye which is (a) capable of being solubilised in the adhesive resin derived by the addition of the acrylic monomer (2) to the urethane elastomer (1) and (b) has at least two tertiary nitrogen atoms linked by one or more conjugated double bonds in its structure.

5 2. An adhesive composition according to claim 1 wherein the elastomer (1) is derivable by reacting (i) a polyether diol with an aromatic diisocyanate to form an isocyanate prepolymer and (ii) the isocyanate prepolymer with a molar excess of an acrylic monomer in the presence of a low molecular weight di(meth)acrylate ester of a glycol.

3. An adhesive composition according to claim 2 wherein (i) the polyether diol is selected from  
10 polyoxyethylene glycol and polyoxypropylene glycol and has a molecular weight from 400-2000, (ii) the aromatic diisocyanate is diphenyl methane diisocyanate, (iii) the isocyanate prepolymer has from 2-20% free isocyanate groups, and (iv) up to 50% molar excess of the acrylic monomer based on the free isocyanate groups in the prepolymer is used for reaction with the prepolymer.

4. An adhesive composition according to claim 2 or 3 wherein the di(meth)acrylate ester is of a glycol  
15 selected from triethylene glycol, tetraethylene glycol, 1,3-butylene glycol and diethylene glycol and the ester is used in an amount from 10-20 parts per hundred parts of the prepolymer.

5. An adhesive composition according to any one of the preceding claims wherein the acrylic monomer (2) is added to the elastomer (1) in an amount from 20-40% w/w of the elastomer.

6. An adhesive composition according to any one of the preceding claims wherein the acrylic monomer  
20 is selected from a vinyl carboxylic acid and hydroxyalkyl(meth)acrylates.

7. An adhesive composition according to any one of the preceding claims wherein the acrylic monomer is selected from hydroxyethylacrylate, hydroxyethylmethacrylate, hydroxypropyl methacrylate, acrylic acid and methacrylic acid.

8. An adhesive composition according to any one of the preceding claims wherein the organic  
25 compound (4) has the formula  $R-SO_2-NH-COR^1$  wherein R is an aliphatic, alicyclic or an aromatic group and where  $R^1$  is an alicyclic or an aromatic group.

9. A process according to any one of the preceding claims wherein the organic sulphinates and their salts suitably have a general formula:



30 where R has the same significance as for a sulphimide defined above and  $R^2$  is either a proton or a monovalent metal ion e.g. ions of the alkali metals.

10. An adhesive composition according to any one of the preceding claims wherein the organic sulphimide, organic sulphinate or a salt thereof is selected from o-benzene sulphimide and a sodium benzene sulphinate.

35 11. An adhesive composition according to any one of the preceding claims wherein the organic sulphimide or salt thereof is used in an equiweight amount (50/50 mixture) with respect to the adhesive resin.

12. An adhesive composition according to any one of the preceding claims wherein the peroxide  
40 initiator (4) is an organic peroxide stable at room temperature and is used in an amount from 1-3 parts per hundred parts of the adhesive resin.

13. An adhesive composition according to any one of the preceding claims wherein the curing accelerator is selected from methylene blue and crystal violet.

14. An adhesive composition according to claim 13 wherein the curing accelerator is used as a quaternary ammonium salt.

45 15. An adhesive composition according to any one of the preceding claims wherein the curing accelerator (5) is used in an amount from 0.1-2 parts per hundred parts of the adhesive resin.

16. An adhesive composition according to claim 1 as hereinbefore described with reference to the Examples.

50

55